

試驗報告



報告編號：TB-22-02197

C-22-05081

頁數：1 OF 1

報告日期：111年05月11日

工程名稱：自測

承 包 商：---

委託單位：顏昌興業有限公司

供料廠商：---

樣品名稱：尺寸30×30×0.8公分超硬石英磚

面磚種類：施釉、內裝地壁磚、乾式、Ib類

加註項目：表面施作袂滑倒防滑劑

送驗人員：顏昌興業有限公司-曹琍淇

收件日期：111年04月22日

試驗日期：111年05月09日~111年05月11日

備註：1.以上資料（樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外）及下述報告內容標示#處係由顧客提供
2.除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製
3.送樣方式：郵寄貨運收件

試驗方法：CNS 3299-12：2011 陶瓷面磚試驗法-第12部：防滑性試驗法

試驗結果：

試體編號	防滑性試驗結果		
	1	2	3
表面狀態	使用自來水做為媒介物，散佈量約400g/m ²		
測試環境溫度(°C)	25.7		
最大值	0.560	0.578	0.574
最小值	0.553	0.573	0.571
C.S.R值穿鞋時之防滑係數	0.56	0.58	0.57

試體編號	防滑性試驗結果		
	4	5	6
表面狀態	使用滑石粉加入約300倍質量之自來水混合成懸濁液做為媒介物，散佈量約100g/m ²		
測試環境溫度(°C)	25.3		
最小值	0.804	0.784	0.799
C.S.R.B值赤腳時之防滑係數	0.81	0.79	0.80

註：本試驗報告之試驗地點同實驗室地址。

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.